



Product information

4CR-Industry 0407-1 AC Universal Hardener fast

Page 1 / 1

Version 1 / February 2020

Product description

Hardener "fast" for 4CR 2K-polyurethan acryl coatings and primers.

Technical specifications

Binder base: Polyisocyanate

Density DIN EN ISO 2811 (kg/l): 0,9 - 1,0

Solids content (% by weight): 38 - 39

Delivery viscosity DIN 53211 4 mm (in s): 13 - 16

Storage

At least 2 years in unopened original container

Processing tips

For professional use only.

This hardener reacts with humidity, therefore close tin immediately after use.

Avoid inhalation of spraying mist.

Cleaning of tools

Clean tools immediately after use with Nitro-Thinner.