



## Product information

# 4CR-Industry 0408-1 AC HS Hardener fast

Page 1 / 1

Version 2 / April 2020

### Product description

High solid Hardener "fast" for 4CR 2K-polyurethan acryl coatings and primers.

### Technical specifications

Binder base: Polyisocyanate

Density DIN EN ISO 2811 (kg/l): 0,9 - 1,0

Solids content (% by weight): 54 - 55

Delivery viscosity DIN 53211 4 mm (in s): 13 - 16

### Storage

At least 2 years in unopened original container.

### Processing tips

For professional use only.

This hardener reacts with humidity, therefore close tin immediately after use.

Avoid inhalation of spraying mist.

### Cleaning of tools

Clean tools immediately after use with Nitro-Thinner.