



Product information

4CR-Industry 0409-351 2K Hardener structure

Page 1 / 1

Version 1 / February 2020

Product description

Special hardener for the application of recommended 4CR-Industry structure paint systems.

Mixing ratio with recommended 4CR-Industry paint systems

Paint	Mixing ratio by Volume	Mixing ratio by weight
72-185 AC 2K Structure Paint silk-gloss/70	4:1	5:1

Technical specifications

Binder base: Polyisocyanate

Density DIN EN ISO 2811 (kg/l): 1,0 - 1,1

Solids content (% by weight): 65 - 66

Delivery viscosity DIN 53211 4 mm (in s): 24 - 26

Storage

At least 2 years in unopened original container.

Processing tips

For professional use only.

This hardener reacts with humidity, therefore close tin immediately after use.

Avoid inhalation of spraying mist.

Cleaning of tools

Clean tools immediately after use with Nitro-Thinner.