according to 1907/2006/EC, Article 31



Printing date 19.02.2020

Version number 1

# SECTION 1: Identification of the substance/mixture and of the company/undertaking

#### · 1.1 Product identifier

- · Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70
- $\cdot$  1.2 Relevant identified uses of the substance or mixture and uses advised against
- No further relevant information available.
- $\cdot$  Application of the substance / the mixture <code>Paint</code>

1.3 Details of the supplier of the safety data sheet
Manufacturer/Supplier: 4CR Vertriebsgesellschaft mbH Oberer Sommerfeldweg 2 D-94469 Deggendorf Tel.: +49 (0) 40 69 60 99 315 Fax: +49 (0) 40 69 60 99 316 E-Mail: Info@4CR.com www.4CR.com
1.4 Emergency telephone number: +49(0)700 24112112 (CRM)

## SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture · Classification according to Regulation (EC) No 1272/2008

GHS02 flame

Flam. Liq. 3 H226 Flammable liquid and vapour.



STOT SE 3 H336 May cause drowsiness or dizziness.

· 2.2 Label elements

#### · Labelling according to Regulation (EC) No 1272/2008

The product is classified and labelled according to the CLP regulation.

· Hazard pictograms



· Signal word Warning

- · Hazard-determining components of labelling:
- n-Butyl acetate

2-Methoxy-1-methylethyl acetate Hydrocarbons, C9, aromatics

· Hazard statements

H226 Flammable liquid and vapour. H336 May cause drowsiness or dizziness.

Precautionary statements

Precautionary stat	ements
P101	If medical advice is needed, have product container or label at hand.
P102	Keep out of reach of children.
P103	Read label before use.
P210	Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
P261	Avoid breathing dust/fume/gas/mist/vapours/spray.

(Contd. on page 2)

<sup>-</sup> GB

Safety data sheet according to 1907/2006/EC, Article 31 **CCR** *Revision: 19.02.2020* 

Printing date 19.02.2020

Version number 1

#### Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

(Contd. of page 1)

P280	Wear protective gloves/protective clothing/eve protection/face protection.
P303+P361+P.	353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water/shower.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
P501	Dispose of contents/container in accordance with local/regional/national/international
	regulations.
· Additional info	rmation:
EUH066 Repea	ted exposure may cause skin dryness or cracking.
EUH208 Conta	ins 2,3-epoxypropyl neodecanoate. May produce an allergic reaction.
· 2.3 Other hazar	ds
· Results of PBT	and vPvB assessment
· <b>PBT:</b> Not applied	cable.

· vPvB: Not applicable.

## **SECTION 3: Composition/information on ingredients**

· 3.2 Chemical characterisation: Mixtures

· Description: Mixture of substances listed below with nonhazardous additions.

· Dangerous components:			
CAS: 123-86-4 EINECS: 204-658-1 Reg.nr.: 01-2119485493-29	n-Butyl acetate Flam. Liq. 3, H226; (INSTOT SE 3, H336)	10-25%	
CAS: 108-65-6 EINECS: 203-603-9 Reg.nr.: 01-2119475791-29	2-Methoxy-1-methylethyl acetate Flam. Liq. 3, H226; () STOT SE 3, H336	2.5-<10%	
CAS: 64742-95-6 EC number: 918-668-5 Reg.nr.: 01-2119455851-35	Hydrocarbons, C9, aromatics Flam. Liq. 3, H226; Asp. Tox. 1, H304; Aquatic Chronic 2, H411; STOT SE 3, H335-H336	1-<2.5%	
CAS: 1330-20-7 EINECS: 215-535-7 Reg.nr.: 01-2119488216-32	Xylene ♦ Flam. Liq. 3, H226; ♦ STOT RE 2, H373; Asp. Tox. 1, H304; ♦ Acute Tox. 4, H312; Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit. 2, H319; STOT SE 3, H335	1-<2.5%	
CAS: 112-07-2 EINECS: 203-933-3 Reg.nr.: 01-2119475112-47	2-Butoxyethyl acetate Acute Tox. 4, H302; Acute Tox. 4, H312; Acute Tox. 4, H332	1-<2.5%	
CAS: 26761-45-5 EINECS: 247-979-2 Reg.nr.: 01-2119431597-33	2,3-epoxypropyl neodecanoate Muta. 2, H341; Aquatic Chronic 2, H411; Skin Sens. 1, H317	<b>≥</b> 0.1-<0.25%	

• Additional information: For the wording of the listed hazard phrases refer to section 16.

# **SECTION 4: First aid measures**

• 4.1 Description of first aid measures

• After inhalation: Supply fresh air; consult doctor in case of complaints.

- After skin contact: Generally the product does not irritate the skin.
- After eye contact: Rinse opened eye for several minutes under running water. Then consult a doctor.
- · After swallowing: If symptoms persist consult doctor.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

(Contd. on page 3)

GB -

according to 1907/2006/EC, Article 31

Printing date 19.02.2020

Version number 1



(Contd. of page 2)

Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

· Information for doctor:

**SECTION 5: Firefighting measures** 

· 5.1 Extinguishing media

• Suitable extinguishing agents: CO2, sand, extinguishing powder. Do not use water.

· For safety reasons unsuitable extinguishing agents: Water with full jet

• 5.2 Special hazards arising from the substance or mixture No further relevant information available.

· 5.3 Advice for firefighters

· Protective equipment: No special measures required.

#### **SECTION 6:** Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Wear protective equipment. Keep unprotected persons away.
- 6.2 Environmental precautions: Do not allow to enter sewers/ surface or ground water.

• 6.3 Methods and material for containment and cleaning up: Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Ensure adequate ventilation.

Do not flush with water or aqueous cleansing agents

• 6.4 Reference to other sections
 See Section 7 for information on safe handling.
 See Section 8 for information on personal protection equipment.
 See Section 13 for disposal information.

# SECTION 7: Handling and storage

• 7.1 Precautions for safe handling Use only in well ventilated areas. Ensure good ventilation/exhaustion at the workplace. Prevent formation of aerosols.

- Information about fire and explosion protection: Keep ignition sources away - Do not smoke. Protect against electrostatic charges.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:
- Requirements to be met by storerooms and receptacles: No special requirements.
- Information about storage in one common storage facility: Store away from foodstuffs.
- Further information about storage conditions: Keep container tightly sealed.

· Storage class: 3

• 7.3 Specific end use(s) No further relevant information available.

## SECTION 8: Exposure controls/personal protection

• Additional information about design of technical facilities: No further data; see item 7.

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

123-86-4 n-Butyl acetate

WEL Short-term value: 966 mg/m<sup>3</sup>, 200 ppm Long-term value: 724 mg/m<sup>3</sup>, 150 ppm

(Contd. on page 4)

GB -

Safety data sheet according to 1907/2006/EC, Article 31



- GB -

Printing date 19.02.2020

Version number 1

Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

100-0	5-6 2-Methoxy-1-methylethyl acetate
WEI	Short-term value: 548 mg/m <sup>3</sup> , 100 ppm
WEL	Long-term value: 274 mg/m <sup>3</sup> , 50 ppm
	Sk
1330-	20-7 Xylene
	Short-term value: 441 mg/m <sup>3</sup> , 100 ppm
	Long-term value: 220 mg/m <sup>3</sup> , 50 ppm
	Sk; BMGV
112-0	7-2 2-Butoxyethyl acetate
WEL	Short-term value: 332 mg/m <sup>3</sup> , 50 ppm
	Long-term value: 133 mg/m <sup>3</sup> , 20 ppm
	Sk
Ingre	dients with biological limit values:
1330-	20-7 Xylene
BMG	V 650 mmol/mol creatinine
	Medium: urine
	Sampling time: post shift
	Parameter: methyl hippuric acid
Addit	ional information: The lists valid during the making were used as basis.
8.2 E.	xposure controls
	nal protective equipment:
	ral protective and hygienic measures: Wash hands before breaks and at the end of work.
	ratory protection: Use suitable respiratory protective device only when aerosol or mist is formed.
	ction of hands:
D (	
the ch	pemical mixture.
the ch The g	emical mixture. love material has to be impermeable and resistant to the product/ the substance/ the preparation.
the ch The g	emical mixture. love material has to be impermeable and resistant to the product/ the substance/ the preparation.
the ch The g Selec	nemical mixture. love material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the
the ch The g Selec degra	nemical mixture. love material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation
the ch The g Selec degra <b>Mater</b> The so and v resista	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. The glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of qualit aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the
the ch The g Selec degra Mater The su and v resista applia	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. The glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation.
the ch The g Selec degra Mater The so and v resist applie Break	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali- aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>athrough time of glove material</b>
the ch The g Selec degra <b>Mater</b> The su and v resista applie <b>Break</b>	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. Tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali- aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>Ethrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be
the ch The g Selec degra <b>Mater</b> The so and v resista applic <b>Break</b> The e obser	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali- aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>ethrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be ved.
the ch The g Selec degra <b>Mater</b> The so and v resista applic <b>Break</b> The e obser	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. Tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>Ethrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be
the ch The g Selec degra <b>Mater</b> The so and v resista applic <b>Break</b> The e obser	nemical mixture. Nove material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>rial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of quali- aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>ethrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be ved.
the ch The g Selec degra <b>Mater</b> The so and v resista applic <b>Break</b> The e obser	tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>ial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of qualitatives aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>cthrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be ved. <b>rotection:</b>
the ch The g Selec degra Mater The so and v resista applic Break The e obser Eye p	Tightly sealed goggles
the ch The g Selec degra Mater The so and v resista applic Break The e obser Eye p	tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>ial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of qualitatives aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the cation. <b>cthrough time of glove material</b> xact break trough time has to be found out by the manufacturer of the protective gloves and has to be ved. <b>rotection:</b>
the ch The g Selec degra Mater The so and v resista applio Break The e obser Eye p	The mical mixture. In the product of the product of the product of the properties of the pro
the ch The g Selec degra Mater The su and v resista applid Break The e obser Eye p SEC 9.1 In	The mical mixture. Note material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation <b>ial of gloves</b> election of the suitable gloves does not only depend on the material, but also on further marks of qualitaries from manufacturer to manufacturer. As the product is a preparation of several substances, the farme of the glove material can not be calculated in advance and has therefore to be checked prior to the sation. <b>chrough time of glove material chrough time has to be found out by the manufacturer of the protective gloves and has to be ved. rotection: Tightly sealed goggles TION 9: Physical and chemical properties</b>
the ch The g Selec degra Mater The s and v resista applid Break The e obser Eye p SEC	The mical mixture. Here material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation trial of gloves election of the suitable gloves does not only depend on the material, but also on further marks of qualit aries from manufacturer to manufacturer. As the product is a preparation of several substances, the funce of the glove material can not be calculated in advance and has therefore to be checked prior to the sation. through time of glove material tanto of gloves and the manufacturer of the protective gloves and has to be found out by the manufacturer of the protective gloves and has to be ved. Tightly sealed goggles Tightly sealed goggles To provide a glove glove sealed goggles
the ch The g Selec degra Mater The s and v resista applid Break The e obser Eye p SEC 9.1 In Gener Apped	The mical mixture. Note that the product of the product of the product of the properties Note that the product of the substance of the properties Note that the product of the substance of the properties Note that the product of the product of the properties Note that the product of the properties Note that the product of the product of the properties Note that the product of the product of the properties Note that the product of the produ
the ch The g Selec degra Mater The s and v resista applid Break The e obser Eye p SEC 9.1 In Gener Apped For	The product of the glove material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation rial of gloves election of the suitable gloves does not only depend on the material, but also on further marks of qualitaries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the form of glove material can not be calculated in advance and has therefore to be checked prior to the cation. Athrough time of glove material time has to be found out by the manufacturer of the protective gloves and has to be ved. Tightly sealed goggles Tightly sealed goggles Tightly sealed goggles Tightly sealed goggles The physical and chemical properties Tail Information on basic physical and chemical properties Tightly sealed material properties The physical and chemical properties The physical physical and chemical properties The physical physical and chemical physical physic
the ch The g Selec degra Mater The s and v resista applid Break The e obser Eye p Eye p SEC 9.1 In Gener Apped For	<pre>memical mixture. love material has to be impermeable and resistant to the product/ the substance/ the preparation. tion of the glove material on consideration of the penetration times, rates of diffusion and the dation ial of gloves election of the suitable gloves does not only depend on the material, but also on further marks of qualit aries from manufacturer to manufacturer. As the product is a preparation of several substances, the ance of the glove material can not be calculated in advance and has therefore to be checked prior to the ration. through time of glove material xact break trough time has to be found out by the manufacturer of the protective gloves and has to be ved. rotection:</pre>

Safety data sheet according to 1907/2006/EC, Article 31



Printing date 19.02.2020

Version number 1

### Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

	(Contd. of page 4
· Odour threshold:	Not determined.
· pH-value:	Not determined.
• Change in condition Melting point/freezing point: Initial boiling point and boiling range.	Undetermined. : 100 °C
· Flash point:	30 °C (DIN 53213)
· Flammability (solid, gas):	Not applicable.
· Ignition temperature:	315 °C (DIN 51794)
· Decomposition temperature:	Not determined.
• Auto-ignition temperature:	Product is not selfigniting.
· Explosive properties:	Product is not explosive. However, formation of explosive air vapour mixtures are possible.
· Explosion limits: Lower: Upper:	1.2 Vol % 7.5 Vol %
· Vapour pressure at 20 °C:	<15 hPa
<ul> <li>Density at 20 °C:</li> <li>Relative density</li> <li>Vapour density</li> <li>Evaporation rate</li> </ul>	1.248 g/cm <sup>3</sup> (DIN 53217) Not determined. Not determined. Not determined.
· Solubility in / Miscibility with water:	Not miscible or difficult to mix.
· Partition coefficient: n-octanol/water:	Not determined.
• Viscosity: Dynamic at 20 °C: Kinematic:	10,000 mPas Not determined.
· Solvent content: Water: VOC (EC)	0.0 % 32.21 %
Solids content (weight-%): • 9.2 Other information	67.8 % No further relevant information available.

# SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

- · 10.2 Chemical stability
- Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.
- · 10.3 Possibility of hazardous reactions No dangerous reactions known.
- · 10.4 Conditions to avoid No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- · 10.6 Hazardous decomposition products: Carbon monoxide

(Contd. on page 6)

GB

according to 1907/2006/EC, Article 31



Printing date 19.02.2020

Version number 1

Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

(Contd. of page 5)

### **SECTION 11: Toxicological information**

- · 11.1 Information on toxicological effects
- $\cdot$  Acute toxicity Based on available data, the classification criteria are not met.

## $\cdot$ LD/LC50 values relevant for classification:

64742-95-6 Hydrocarbons, C9, aromatics

*Oral LD50* >2,000 mg/kg (rat)

Dermal LD50 >2,000 mg/kg (rabbit)

- · Primary irritant effect:
- · Skin corrosion/irritation Based on available data, the classification criteria are not met.
- Serious eye damage/irritation Based on available data, the classification criteria are not met.
- · Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- · CMR effects (carcinogenity, mutagenicity and toxicity for reproduction)
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.
- Carcinogenicity Based on available data, the classification criteria are not met.
- Reproductive toxicity Based on available data, the classification criteria are not met.
- · STOT-single exposure
- May cause drowsiness or dizziness.
- STOT-repeated exposure Based on available data, the classification criteria are not met.
- Aspiration hazard Based on available data, the classification criteria are not met.

#### **SECTION 12: Ecological information**

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- · 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- Additional ecological information:
- · General notes:

Water hazard class 1 (German Regulation) : slightly hazardous for water

Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

- · 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · vPvB: Not applicable.
- · 12.6 Other adverse effects No further relevant information available.

## **SECTION 13: Disposal considerations**

#### · 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

#### · European waste catalogue

08 01 11\* waste paint and varnish containing organic solvents or other hazardous substances

- Uncleaned packaging:
- · Recommendation: Disposal must be made according to official regulations.

(Contd. on page 7)

GB

according to 1907/2006/EC, Article 31



(Contd. of page 6)

Printing date 19.02.2020

Version number 1

Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

**SECTION 14: Transport information** · 14.1 UN-Number · ADR, IMDG, IATA UN1263 · 14.2 UN proper shipping name UN1263 PAINT · ADR · IMDG, IATA PAINT · 14.3 Transport hazard class(es) · ADR · Class 3 (F1) Flammable liquids. · Label 3 · IMDG, IATA · Class 3 Flammable liquids. · Label 3 ·14.4 Packing group · ADR, IMDG, IATA Ш · 14.5 Environmental hazards: • Marine pollutant: No · 14.6 Special precautions for user Warning: Flammable liquids. · Danger code (Kemler): 30 · EMS Number: F-E,S-E· Stowage Category Α · 14.7 Transport in bulk according to Annex II of Marpol and the IBC Code Not applicable. · Transport/Additional information: · ADR · Transport category 3 • Tunnel restriction code D/E· Remarks: ≤ 450 l: 2.2.3.1.5 ADR · IMDG · Limited quantities (LQ) 5L· Remarks: ≤ 5 l: 2.2.3.1.5 IMDG · UN "Model Regulation": UN 1263 PAINT, 3, III

# SECTION 15: Regulatory information

 $\cdot$  15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Directive 2012/18/EU

- · Named dangerous substances ANNEX I None of the ingredients is listed.
- · Seveso category P5c FLAMMABLE LIQUIDS

(Contd. on page 8)

GB

according to 1907/2006/EC, Article 31



(Contd. of page 7)

Printing date 19.02.2020

Version number 1

Trade name: 4CR 72-185 AC 2K Structure Paint silk-gloss/70

- · Qualifying quantity (tonnes) for the application of lower-tier requirements 5,000 t
- $\cdot \tilde{Q}$  ualifying quantity (tonnes) for the application of upper-tier requirements 50,000 t
- · REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3

· National regulations:

Class	Share in %
NK	25-50

· 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

#### **SECTION 16: Other information**

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

#### · Relevant phrases

H226 Flammable liquid and vapour.

H302 Harmful if swallowed.

H304 May be fatal if swallowed and enters airways.

H312 Harmful in contact with skin.

H315 Causes skin irritation.

H317 May cause an allergic skin reaction.

H319 Causes serious eye irritation.

H332 Harmful if inhaled.

H335 May cause respiratory irritation.

H336 May cause drowsiness or dizziness.

H341 Suspected of causing genetic defects.

H373 May cause damage to organs through prolonged or repeated exposure.

H411 Toxic to aquatic life with long lasting effects.

#### · Classification according to Regulation (EC) No 1272/2008

The classification of the mixture is generally based on the calculation method using substance data according to Regulation (EC) No 1272/2008.

• Abbreviations and acronyms:

RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulations Concerning the International Transport of Dangerous Goods by Rail) ICAO: International Civil Aviation Organisation

ADR: Accord européen sur le transport des marchandises dangereuses par Route (European Agreement concerning the International Carriage of Dangerous Goods by Road)

IMDG: International Maritime Code for Dangerous Goods

IATA: International Air Transport Association

GHS: Globally Harmonised System of Classification and Labelling of Chemicals

EINECS: European Inventory of Existing Commercial Chemical Substances

ELINCS: European List of Notified Chemical Substances

CAS: Chemical Abstracts Service (division of the American Chemical Society)

VOC: Volatile Organic Compounds (USA, EU)

LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent

*PBT: Persistent, Bioaccumulative and Toxic* 

*vPvB: very Persistent and very Bioaccumulative* 

Flam. Liq. 3: Flammable liquids – Category 3

Acute Tox. 4: Acute toxicity – Category 4

Skin Irrit. 2: Skin corrosion/irritation – Category 2

Eye Irrit. 2: Serious eye damage/eye irritation – Category 2

Skin Sens. 1: Skin sensitisation – Category 1

Muta. 2: Germ cell mutagenicity – Category 2 STOT SE 2: Specific target argen torigin (single

STOT SE 3: Specific target organ toxicity (single exposure) – Category 3 STOT RE 2: Specific target organ toxicity (repeated exposure) – Category 2

STOT RE 2: Specific target organ toxicity (repeated exposure) – Category 2 Asp. Tox. 1: Aspiration hazard – Category 1

Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard – Category 2